

# AQUASTRIP

## TECHNICAL DATA SHEET

### Product description

Paint stripping gel with solvents with low environmental impact. Specifically formulated for the removal of old antifoulings from wood, iron, plastic and metal surfaces in general. Good softening power also for enamels, varnishes and mono-component substrates. Thanks to its formulation, the product does not affect the gelcoat or fiberglass. AQUASTRIP allows to treat large surfaces such as the hull in a single pass without any danger for the boat. The product is free from toxic or harmful substances.

### Product information

Colour	Light green		
Specific gravity	UNI EN ISO 2811-1	1,00 – 1,20 g/cm <sup>3</sup>	
Flash point	UNI EN ISO 13736	20 °C	
Packaging	2,5 Lt		

### Application and use


#### SURFACE PREPARATION

Homogenise the product before usage. Apply on the surface 2-3 mm of product at least and leave on for 2 or 3 hours, in base of the external temperature. The surface must not be exposed to direct sunlight. Use a scraper or high pressure water to remove the soft mixture of AQUASTRIP and paint. If necessary, repeat the operation. Before painting, the surface must be washed thoroughly with water and allowed to dry. Sand down with grit paper 120 - 180. Rinse and allow the surface to dry well before repainting.

# AQUASTRIP

## TECHNICAL DATA SHEET

### Application data

Thinner/Tool cleaning		Alcool or thinner
Application method		
Theoretical coverage	2 – 3 m <sup>2</sup> /liter	

### CONDITIONS DURING APPLICATION

During the application and the reaction period, the ambient temperature must not be less than 5° C and must not exceed 30° C. Make sure there is enough ventilation when application takes place in closed areas.

### Storage

It is recommended to avoid exposure to air and extreme temperatures. To maximize the shelf life in the can, it is worth checking that the container is well closed during the storage and the temperature is between 5° C and 35° C. Avoid exposure to direct sunlight.

# AQUASTRIP

## TECHNICAL DATA SHEET

### Safety rules

---

Observe the provisions of DPR 303 and 547. Avoid contact with the skin, for example. Operate in well ventilated places and, if in closed areas, use vacuum cleaners, fans and air conveyors. During the application, use appropriate protections (masks, gloves, glasses, etc.). Before using, read sections 7-8 of the SDS.

#### INSTRUCTIONS FOR THE DISPOSAL OF PRODUCTS AND PACKAGING

Empty packaging that contained products: Dispose of empty packaging according to the requirements of the waste disposal law, for example by taking them to a recycling centre.

Packages containing the unused products: Dispose of the unused product in accordance with the law of disposal of such waste, for example by taking it to a recycling center, recycling of packaging is prohibited in this case. Do not empty into drains or watercourses. Product packaging must be kept indoor, and the temperature in the storage place must be between 10° C and 35 °C. Do not expose to sunlight.

### Notes

---

The values indicated in the present technical sheet can have slight variations from one batch to another. The applied product must not come in contact with water, chemicals or be subjected to mechanical stress before the curing is complete. Wet film thicknesses refer to a product that has not been diluted. With dilution, this value will rise. The above information is the result of accurate laboratory tests and practical experience; however, since the product is predominantly used outside the manufacturer's control. Boero Bartolomeo S.p.A can only guarantee its quality. The information contained in this sheet may be subject to revision by the Company. For clarification, updates or further information, it is recommended to contact Boero Bartolomeo S.p.A directly. The present datasheet annuls and replaces every other precedent to this one.