

# ANTISKID POWDER

## TECHNICAL DATA SHEET

### Product description

---

Antiskid powder is a special granulated powder of plastic material. It is odourless and can be used as antiskid additive for watercraft floor and/or deck paintings. It can boast excellent mechanical characteristics and resistance to marine environment.

### Product information

---

Finish	Powder	
Colour	Colourless	
Solids (by volume)	ASTM D2369	100%
Specific gravity	UNI EN ISO 2811-1	0,9 ± 0,2 g/cm <sup>3</sup>
Packaging	0,15 kg	

### Application and use

---

#### SURFACE PREPARATION

Add the product to the topcoat that has already been catalysed. Its percentage can range from 4% to 5% by volume depending on the needs. Thoroughly mix before and during application.

#### APPLICATION PROCEDURE

Generally, a 4-5% addition by volume in the product ready to use allows the application of two coats. As a result, the effect will be functioning and aesthetically pleasant. The painting with additives must be often mixed: granular material tends to float.

Always apply 2 coats. The 0,15 kg packaging allows to obtain from 3 to 5 litres of ready to use antiskid product.

# ANTISKID POWDER

## TECHNICAL DATA SHEET

### Storage

---

It is recommended to avoid exposure to air and extreme temperatures. To maximize the shelf life in the can, it is worth checking that the container is well closed during the storage and the temperature is between 10° C and 35° C. Avoid exposure to direct sunlight.

### Safety rules

---

Observe the provisions of DPR 303 and 547. Avoid contact with the skin, for example. Operate in well ventilated places and, if in closed areas, use vacuum cleaners, fans and air conveyors. During the application, use appropriate protections (masks, gloves, glasses, etc.). Before using, read sections 7-8 of the SDS.

#### INSTRUCTIONS FOR THE DISPOSAL OF PRODUCTS AND PACKAGING

Empty packaging that contained products: Dispose of empty packaging according to the requirements of the waste disposal law, for example by taking them to a recycling centre.

Packages containing the unused products: Dispose of the unused product in accordance with the law of disposal of such waste, for example by taking it to a recycling centre, recycling of packaging is prohibited in this case. Do not empty into drains or watercourses. Product packaging must be kept indoor, and the temperature in the storage place must be between 10° C and 35 °C. Do not expose to sunlight.

### Notes

---

The values indicated in the present technical sheet can have slight variations from one batch to another. The applied product must not come in contact with water, chemicals or be subjected to mechanical stress before the curing is complete. Wet film thicknesses refer to a product that has not been diluted. With dilution, this value will rise. The above information is the result of accurate laboratory tests and practical experience; however, since the product is predominantly used outside the manufacturer's control. Boero Bartolomeo S.p.A can only guarantee its quality. The information contained in this sheet may be subject to revision by the Company. For clarification, updates or further information, it is recommended to contact Boero Bartolomeo S.p.A directly. The present datasheet annuls and replaces every other precedent to this one.